Technical Data Sheet

Conductive Hybrid Paste Ink TEC-PA-070 For Screen Printing Process

Product Description

'TEC-PA-070 is a hybrid paste ink which is specially designed by InkTec's outstanding technology and research solution for the purpose of firing in low temperature. It is hybrid paste ink and has strong adhesion even on ITO coated substrates. It enables you to apply various fields in the electronic industry.

Product Features

• Simple process

Printing method can reduce the manufacturing processes with only printing and sintering compare with etching process. Simple process will make it possible for you to retrench cost of processes.

Short time for sintering

It takes a short period of time around 20 min/130°C for sintering, so it can improve your productivity.

Storage

• Stored at refrigeration(0°C~5°C)

Performance Specification Data

• Ink Properties

Items	Representative Values	Remarks
Ink Type	Paste	-
Appearance	Gray	Visual
Viscosity	20 rpm : 150,000	BROOKFIELD,
		DV-II +PRO
		(Spindle : 15,
		at 25°C)
Printing	Flat or Rotary	
Method	Screen	
Density	3.17 ± 0.2 g/cm ³	at 25℃
Total Solid	83wt%	TGA
Contents		

Performance Data

Items	Representative Values	Remarks
Curing Temperature	130°C (20min)	in air
Sheet Resistivity	120 mΩ/sq.	@25μm
Volume Resistivity	3.0 X 10 ⁻⁴ Ω.cm	-
Adhesion (ITO Film)	Min. 4B	ASTM D3359 rating
Substrates	ITO Film	-


E-mail: ei@inktec.com / http://www.inktec.com


Usage & Notes for handling


- Use of original paste is recommended. If dilution is needed, please use exclusive solvent, DA-030 or 2-(2-Ethoxytethoxy)ethyl acetate (CAS NO 112-15-2)
- If the paste was stored for a long time, conductive metal power may precipitate. Full stirring based on our guidance should be done before use

Applications

InkTec hybrid paste ink for ITO coated substrates is applicable to wire or electrode materials in the display (OLED, LCD, PDP) & solar cell fields using screen printing.







Important Notice to User

Information presented in this technical data sheet is considered reliable, but conditions and methods of use, which are beyond our control, may modify results. Before adopting our products for commercial use, the user should confirm their suitability. In no case should recommendations or suggestions for the use of our products be understood to sanction violation of any patent. All information contained in this data sheet is given in good faith but without warranty or guarantee of any kind whatever, whether implied or expressed.

E-mail: ei@inktec.com/http://www.inktec.com